


Magnet Specifications

300-01-022 NEO 35 SH MATERIAL SPECS(25°C):	TYPICAL:	MINIMUM:
PROCESSING TYPE:	SINTERED	
BR GAUSS:	12000	11700
HC OERSTED:	11500	11000
HCI OERSTED:	20000	21000
BHMAX MGOE:	35	33
BR TEMP CO (%/°C):	-0.10	
RECOIL PERM. (UREC):	.19%	
TC CURIE TEMP (°C):	310	
MAX OPERATING TEMP (°C):	150	
Rev A PLATING, NI (MILS):	0.6	0.4

FIELD STRENGTH CLOSE TO MAGNET



FIELD STRENGTH FAR FROM MAGNET

